

SCL-HK 11

Water-based Sublimation ink
for industrial transfer printing



Sublimation Textile



TECHNICAL DATA SHEET

isonik

SCL-HK 11

Water-based Sublimation ink
for industrial transfer printing



KYOCERA



HIGH SPEED
EQUIPMENT



SPECIFIC
FOR FASHION



SPORTSWEAR
SPORTS
EQUIPMENT



TRANSFER
PRINTING



FOR COATED
AND UNCOATED PAPER



BRIGHT AND
VIBRANT COLOURS



STORAGE
CONDITIONS:
AT 5-30°C
TEMPERATURE
DRY AND
WELL-VENTILATED
ENVIRONMENT



PRINTING
CONDITIONS:
20-25°C
TEMPERATURE
40-60%RH
HUMIDITY
RANGE



SEA FREIGHT
SHIPMENT
CONDITIONS
5-30°C
TEMPERATURE
REFRIGERATED
CONTAINER FOR
LONG DISTANCE



AVAILABLE
PACKAGING
10 KG AND
20 KG TANKS



TRANSFER
CONDITIONS
200-210°C
FOR 35-45 SEC



HEAT-SENSITIVE
PRODUCT
DO NOT EXCEED 30°C
AVOID DIRECT
SUNLIGHT



Product description

ISONIK® SCL-HK 11 is a water-based digital sublimation ink for transfer printing. It is suitable for most of the printers equipped with Kyocera KJ4B print heads.

The long-run tests performed on different printers have shown outstanding performances, so that ISONIK SCL-HK 11 is the right choice for industrial printing facilities based on high-speed equipment.

ISONIK SCL-HK 11 is suitable for 100% polyester fabrics or in blends with different fibers with minimum of 70% of PES. It can be used also on any substrate (alu, wood, ceramic, glass, etc.) usually unsuitable for sublimation process, after pretreating with polyester-polyamide resins.

Instructions

- ISONIK SCL-HK 11 is ready to use.
- Keep ISONIK SCL-HK 11 at printing room temperature at least 24 h before use.
- Shake gently before use.
- Follow instructions on label and MSDS.
- Transfer conditions by using a calender or a flat press: temperature 200-210°C for 35/45 sec.
- Care about correct and regular printer maintenance.
- Preliminary tests are recommended to set the best operating parameters (T°C/t sec) to achieve the desired result. Product performance might vary according to the employed hardware, software and the applied printing method.

Notes

- Information regarding fastness and additional technical features is available upon request
- Customized colours are available upon request



DISCLAIMER

The information included in this document is based on experience and the current state of our knowledge and is not intended to be completely exhaustive. The product is for professional use only. Due to multiple factors that could influence the application aspects of ISONIK SCL-HK 11 and thus the final result obtained, Isocarbo suggests to always carry out preliminary tests in order to evaluate possible abnormal behaviour of the products under particular operating conditions different from those stated in this document. Therefore, Isocarbo assumes no responsibility for any differences in the performance of ISONIK SCL-HK 11 and for any loss or damage suffered by persons or property as a result of the information contained in this document. Furthermore, Isocarbo accepts no responsibility for any damage caused to third parties as a result of improper use of ISONIK SCL-HK 11 by any person or company. Isocarbo assures its commitment to the continuous development and improvement of the product and assumes the right to change and update the contents of this technical document at any time.

isonik
YOUR BEST PERFORMANCE

www.isocarbo.it

Made in Italy

isocarbo

Via per Albate, 4
22070 Senna Comasco (CO) Italy
Ph +39 031 507307
info@isocarbo.it